

Elecolit ® 3036 is a silver-filled, solvent-free 2K epoxy resin adhesive with a potlife of 2-3 hours. The mixing ratio is 1:1 w/w. This adhesive may be processed with dispensers, stamps or through screen printing. Curing occurs at room temperature already, increased heat yields very short curing times.

Elecolit ® 3036 provides optimum solutions for cold curing applications thanks to excellent conductivity and gap filling attributes.

Thanks to its lower filling level Elecolit ® 3036 is the more reasonably priced alternative compared to Elecolit ® 3025.

**Shelf life:**

6 months at 5°C

**Technische Daten :**

Color	silver
Resin	epoxy
Filler	silver

**UNCURED PROPERTIES**

Viscosity		paste-like
Flash point		-
Pot-Life [min.]	PE-Norm P019	approx. 120
Density [g/cm³]	PE-Norm P003	approx. 2.8

**Curing**

16	hours at	25	°C	0.02 Ohm x cm
2	hours at	50	°C	
30	minutes at	100	°C	
15	minutes at	120	°C	
5	minutes at	150	°C	0.001 Ohm x cm

**CURED PROPERTIES**

Temperature Resistance [°C]	PE-Norm P030	-40 to 150
Hardness [Shore D]	PE-Norm P052	70 to 80
Volume resistivity [Ohm x cm]	ASTM-D-257-93	0.1
Water Absorption [mass-%]	PE-Norm P053	< 0.5
Tg [°C] (DSC)	PE-Norm P009	75 to 85
CTE [ppm/K]	PE-Norm P017	37
Thermal conductivity [W/m·K]	ASTM 1530	2.7

Our data sheets have been compiled to the best of our knowledge. The information included in our data sheets is exclusive information for the tended user and describes characteristics, with no declaration of commitment. We recommend trials in order to confirm that our products satisfy the particular application requirements. For an additional technical consultation, please contact our RD department. In general, for guarantee claims, please refer to our standard terms and conditions.

**Adhesives  
and more...**

## Mechanical Data

Lap Shear Strength (Stahl/Stahl, 15' 120°C) [MPa]	[PE-Norm P013]	approx. 17.4
Lap Shear Strength (Stahl/Stahl, RT Härtung) [MPa]	[PE-Norm P013]	approx. 13.1

## Instructions for Use

### Surface Preparation

The surfaces to be bonded should be free of dust, oil, fat or any other dirt in order to optimise reproducible results. Lightly soiled surfaces can be cleaned with cleaner IP to create a suitable working surface.

### Application

Our Elecolit 2-C products are delivered in separate packing units. Resins can crystallize at deep temperature storage- this process will be reversible by heating for 1 hour at 40 °C.

The components A and B have to be homogenised well, weigh out in mixing ration and homogenised with each other for min. 2 minutes.

From now, the pot life time starts and the adhesive has to be applied rapidly.

You can dispense or use them for screen printing processes.

### Curing

For curing heat must be applied. In some cases they will cure even at room temperature. But higher temperature will reduce the curing time. For detailed curing information, please look into the technical data sheet. Higher curing temperature will lead to better electrical conductivity and less volume resistivity.

If help is required, please contact our engineering department.

Please read the corresponding **Safety Data Sheet** for this product.