

# Technical Datasheet

## Structalit<sup>®</sup> 5810



### Product Description

Panacol Structalit<sup>®</sup> adhesives are solvent free single or two-component adhesives. They are mostly based on epoxy resin and can be cured at room temperature or by exposure of heat. Structalit<sup>®</sup> products are designed for bonding, casting and protecting components in electronic and automotive industry.

Structalit<sup>®</sup> 5810 is suitable for bonding, coating and potting of metals, glass and many plastics. Structalit<sup>®</sup> 5810 has good adhesion to PC in case of thermal shock. Structalit<sup>®</sup> 5810 has good moisture and chemical resistance.

### Curing Properties

This product is a two-component adhesive. The adhesive can be cured at room temperature or thermally under exposure to heat after mixing the two components in the ratio indicated. Possible curing temperatures are listed in the table below.

Thermal curing	
Time at 25°C	24 h
Time at 80°C	45 min
Time at 120°C	20 min
Time at 150°C	5 min

The adhesive can be applied after mixing the components within the pot life. To determine the pot life, the time it takes to double the increase in viscosity after mixing of the two components is used.

Curing	
Pot life	7 h
Mixing ratio	2:1
Initial strength	24 h
Final strength	48 h

The curing times given are guidelines. They refer to the curing of 2 g of adhesive. The heating up of the joining members are not taken into account.

The final strength of the adhesive is reached at the earliest after 24 h.

### Technical Data

Resin  
Appearance

epoxy  
transparent

### Uncured material

Viscosity mix [mPas] (Brookfield LVT, 25°C) <i>PE-Norm 001</i>	2 000 - 3 000
Viscosity part A [mPas] (Brookfield LVT, 25°C) <i>PE-Norm 001</i>	900 - 1 300
Viscosity part B[mPas] (Brookfield LVT, 25°C) <i>PE-Norm 001</i>	3 000 - 4 000
Density [g/cm <sup>3</sup> ] <i>PE-Norm 004</i>	1,09
Flash point [°C] <i>PE-Norm 050</i>	>100
Refractive index [nD20] <i>PE-Norm 018</i>	1,568

### Cured material

Hardness shore D <i>PE-Norm 006</i>	65 - 80
Temperature resistance [°C]	-40 - 180
Shrinkage [%] <i>PE-Norm 031</i>	<1
Water absorption [mass %] <i>PE-Norm 016</i>	<1

Glass transition temperature DSC [°C] <i>PE-Norm 009</i>	55 - 60
Coefficient of thermal expansion [ppm/K] below Tg <i>PE-Norm 017</i>	60
Coefficient of thermal expansion [ppm/K] above Tg <i>PE-Norm 017</i>	247

Dielectric constant [10kHz]	4
Volume resistivity [Ohm*cm] <i>PE-Norm 040</i>	1,00E+14

Young's modulus E [MPa] <i>PE-Norm 056</i>	2 882
Tensile strength [MPa] <i>PE-Norm 014</i>	21
Elongation at break [%] <i>PE-Norm 014</i>	1
Lap shear strength (Al/Al) [MPa] <i>PE-Norm 013</i>	9
Lap shear strength (steel/steel) [MPa] <i>PE-Norm 013</i>	18
Lap shear strength (brass/brass) [MPa] <i>PE-Norm 013</i>	12

### Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Other packages	at room temperature max. 25°C	at room temperature max. 25°C	at delivery min. 6 months max. 12 months

**\*Store in original, unopened containers!**

### Instructions for Use

#### Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IP® Panacol. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

#### Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve. If help is required, please contact our application engineering department.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

For safety information refer to our safety data sheet.

### Disclaimer

The product is free of heavy metals, PFOS and Phthalates and is conform to the EU-Directive 2017/2102/EU "RoHS III".

**THE VALUES NOTED IN THIS TECHNICAL DATA SHEET ARE TYPICAL PROPERTIES AND ARE NOT MEANT TO BE USED AS PRODUCT SPECIFICATIONS.**

The information contained in this data sheet is believed to be accurate and is provided for information only. Panacol makes no representation or warranties of any kind concerning this information. It is the user's responsibility to determine the suitability of this product for any intended use. Panacol does not assume responsibility for test or performance results obtained by the user. The user assumes all risk and liability connected with the use of this product.

The user should adopt such precautions and use guidelines as may be advisable for the protection of property and persons against any hazards that may be involved in this product's handling or use. Panacol specifically disclaims any liability for consequential or incidental damages of any kind arising from the handling or use of this product. The information contained in this Technical Data Sheet offers no assurance that the product use, application, or process will not infringe on existing patents or licenses of others. Nothing in this Technical Data Sheet transfers or grants license for the use of any patents, trade secrets, intellectual property, or confidential information that is the property of Panacol.

Except as otherwise noted, all trademarks in this document (identified as ®) are the property of Panacol.

### Contact

Panacol-Elosol GmbH  
Daimlerstr. 8  
61449 Steinbach  
Germany  
Phone.: +49 6171 6202-0  
Mail: [info@panacol.de](mailto:info@panacol.de)  
[www.panacol.com](http://www.panacol.com)

Panacol-USA, Inc.  
142 Industrial Lane  
Torrington CT 06790  
USA  
Phone: +1 860-738-7449  
Mail: [info@panacol-usa.com](mailto:info@panacol-usa.com)  
[www.panacol-usa.com](http://www.panacol-usa.com)

Panacol-Korea Co., Ltd.  
#707, Kranz Techno, 388 Dunchon-daero  
Junwon-gu, Seongnam  
Gyeonggi-do, 13403 KOREA  
Phone: +82 31 749 1701  
Mail: [info@panacol-korea.com](mailto:info@panacol-korea.com)  
[www.panacol-korea.com](http://www.panacol-korea.com)

Eleco Panacol – EFD  
125, av Louis Roche  
Z.A. des Basses Noëls  
92238 Gennevilliers Cdx FRANCE  
Tél.: +33 (0)1 47 92 41 80  
Mail: [eleco@eleco-panacol.fr](mailto:eleco@eleco-panacol.fr)  
[www.eleco-panacol.fr](http://www.eleco-panacol.fr)