

# Technical Datasheet

## Vitralit® UD 8559 LV



### Product Description

Panacol Vitralit® adhesives are one-component, solvent-free radiation-curing adhesives. The advantages are very short curing times, good adhesion to a variety of substrates, and easy handling. Vitralit® products are used in electronics, medical applications, optics and for fixing parts in general.

Vitralit® UD 8559 LV is a UV and light-curing acrylate-based adhesive. Vitralit® UD 8559 LV adheres to many plastics and metals and is very suitable as a potting compound and for coating components. Full performance of the Vitralit® UD 8559 LV will be achieved after a few days. The actual curing speed, especially in shade areas, depends on environmental moisture.

### Curing Properties

UV-A	VIS	Thermal curing	Humidity curing
✓	✓	-	✓

✓ suitable      - not suitable

The product cures within seconds with radiation in the UV-A - (320 nm - 390 nm) and visible range (405 nm). For rapid and high quality crosslinking we recommend the UV devices manufactured by Dr. Hoenle AG, which complement our adhesive technology.

UV-curing (Hoenle Discharge lamp, 320-450nm)		
Intensity [mW/cm <sup>2</sup> ]	Layer thickness [mm]	Time [sec]
40	0,1	5

VIS-curing (Hoenle LED Spot 100, 405nm)		
Intensity [mW/cm <sup>2</sup> ]	Layer thickness [mm]	Time [sec]
250	0,1	1

To obtain full cure at least one substrate must be transparent to the recommended wavelength. The curing speed will depend on the intensity of light, light source, the exposure time, and the light transmittance of the substrate.

### Technical Data

Resin  
Appearance

acrylate – PU - hybrid  
translucent

# Technical Datasheet

## Vitralit® UD 8559 LV



### Uncured material

Viscosity [mPas] (Brookfield LVT, 25°C, Sp 3, 30rpm) <i>PE-Norm 001</i>	700 - 1 000
Density [g/cm <sup>3</sup> ] <i>PE-Norm 004</i>	1,05
Flash point [°C] <i>PE-Norm 050</i>	>100
Refractive index [nD20] <i>PE-Norm 018</i>	1,4918

### Cured material

	Shore Hardness D
Initial, after UV cure*	5,3
+ 1 day humidity cure**	13,0
+ 2 days humidity cure	13,1
+ 5 days humidity cure	23,4
+ 6 days humidity cure	27,1
+ 7 days humidity cure	33,4
+ 8 days humidity cure	42,4
+ 9 days humidity cure	44,8
+ 12 days humidity cure	53,0
+ 13 days humidity cure	57,0
+ 14 days humidity cure	65,4
+ 15 days humidity cure	66,0
+ 16 days humidity cure	66,0
+ 19 days humidity cure	67,7
+ 20 days humidity cure	67,1

\*UV cure: UVA lamp, Fe-doped, 60 mW/cm<sup>2</sup>, 30 s.

\*\* Humidity cure: 25 °C, 50 % RH.

Temperature resistance [°C]	-40 - 200
Shrinkage [%] <i>PE-Norm 031</i>	<2
Water absorption [mass %] <i>PE-Norm 016</i>	<1

Glass transition temperature DSC [°C] <i>PE-Norm 009</i>	76
Coefficient of thermal expansion [ppm/K] below Tg <i>PE-Norm 017</i>	42
Coefficient of thermal expansion [ppm/K] above Tg <i>PE-Norm 017</i>	281

Young's modulus E [MPa] <i>PE-Norm 056</i>	1 740
Tensile strength [MPa] <i>PE-Norm 014</i>	39
Elongation at break [%] <i>PE-Norm 014</i>	3

### Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Cartridge	at room temperature max. 25°C	at room temperature max. 25°C	at delivery min. 1,5 months; max. 3 months
Other packages			

**\*Store in original, unopened containers!**

### Instructions for Use

#### Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IP® Panacol. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

#### Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve. If help is required, please contact our application engineering department.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

After application, bonding of the parts should be done quickly. Vitralit® adhesives cure slowly in daylight. Therefore, we recommend to expose the material to as little light as possible and the use of opaque hose lines and dispensing needles.

For safety information refer to our safety data sheet.

### Disclaimer

The product is free of heavy metals, PFOS and Phthalates and is conform to the EU-Directive 2017/2102/EU "RoHS III".

**THE VALUES NOTED IN THIS TECHNICAL DATA SHEET ARE TYPICAL PROPERTIES AND ARE NOT MEANT TO BE USED AS PRODUCT SPECIFICATIONS.**

The information contained in this data sheet is believed to be accurate and is provided for information only. Panacol makes no representation or warranties of any kind concerning this information. It is the user's responsibility to determine the suitability of this product for any intended use. Panacol does not assume responsibility for test or performance results obtained by the user. The user assumes all risk and liability connected with the use of this product.

The user should adopt such precautions and use guidelines as may be advisable for the protection of property and persons against any hazards that may be involved in this product's handling or use. Panacol specifically disclaims any liability for consequential or incidental damages of any kind arising from the handling or use of this product. The information contained in this Technical Data Sheet offers no assurance that the product use, application, or process will not infringe on existing patents or licenses of others. Nothing in this Technical Data Sheet transfers or grants license for the use of any patents, trade secrets, intellectual property, or confidential information that is the property of Panacol.

Except as otherwise noted, all trademarks in this document (identified as ®) are the property of Panacol.

### Contact

Panacol-Elosol GmbH  
Daimlerstr. 8  
61449 Steinbach  
Germany  
Phone.: +49 6171 6202-0  
Mail: [info@panacol.de](mailto:info@panacol.de)  
[www.panacol.com](http://www.panacol.com)

Panacol-USA, Inc.  
142 Industrial Lane  
Torrington CT 06790  
USA  
Phone: +1 860-738-7449  
Mail: [info@panacol-usa.com](mailto:info@panacol-usa.com)  
[www.panacol-usa.com](http://www.panacol-usa.com)

Panacol-Korea Co., Ltd.  
#707, Kranz Techno, 388 Dunchon-daero  
Junwon-gu, Seongnam  
Gyeonggi-do, 13403 KOREA  
Phone: +82 31 749 1701  
Mail: [info@panacol-korea.com](mailto:info@panacol-korea.com)  
[www.panacol-korea.com](http://www.panacol-korea.com)

Eleco Panacol – EFD  
125, av Louis Roche  
Z.A. des Basses Noëls  
92238 Gennevilliers Cdx FRANCE  
Tél.: +33 (0)1 47 92 41 80  
Mail: [eleco@eleco-panacol.fr](mailto:eleco@eleco-panacol.fr)  
[www.eleco-panacol.fr](http://www.eleco-panacol.fr)